



### PRODUCT SPECIFICATION SHEET

## High Gloss Finish

Item No. FCHFF7

#### Description:

High Gloss, Superior Build, Durable Finish -

#### Features & Benefits:

- Optimal value and performance.
- Reduced labor - Fast build with fewer coats.
- Deep gloss.
- 0.0% Free Styrene

#### Directions:

Recommended for use on all types of resilient tile flooring and properly prepared hard surfaces.

**RESTORATIVE MAINTENANCE:** Completely remove all old wax, finish and soil from floor surface following strip procedure instructions on stripper label. Floor surface must be clean, dry and free of residue before finish is applied. Rinse with clean water if necessary. Apply finish in uniform, thin to medium coats using a clean synthetic finish mop, microfiber mop or applicator system. Allow each coat to dry thoroughly before applying additional coats, usually 20 - 30 minutes. Elevated temperatures, heavy coats and humidity may extend dry time. A minimum of 4 coats of finish is recommended. Note: This product is a self-sealing finish, however, if tile is old, worn or porous, initially applying 1 - 2 coats of a sealer will enhance gloss and long term performance.

**ROUTINE MAINTENANCE:** Sweep large debris and dust mop. Damp mop or automatic scrub using a floor cleaner. Buff or burnish the floor to enhance gloss as needed. Use cleaner/restorer to condition the floor and extend the time between top scrub and recoating.

**INTERIM MAINTENANCE:** Sweep large debris and dust mop. Top scrub the floor using scrub and maroon pad or equivalent to remove the top soiled layers of finish. Floor surface must be clean, dry and free of residue before finish is applied. Apply 1 - 2 coats of finish as directed above. Note: Slip resistance meets or exceeds standard, (ASTM D 2047-11) James Machine 0.5 minimum.

**Ideal for use in:** • Mop and bucket, Auto Scrubber



#### Specifications-

Color (liquid)	White
Color (dried)	Crystal clear
Scent	Mild
	8.1 - 8.9
Coverage	2000 Sq. Ft. per gallon
Dry time	20 - 30 minutes
Freeze/ thaw stability	3 cycles
Leveling	Excellent
Gloss (ASTM D 1455-87)	1 coat 75-80, 2 coats 80-85
Specific gravity	1.03
Heel mark resistance	Excellent
Powdering resistance	Excellent
Recoat	Excellent

#### Ingredients:

Water (7732-18 -5); Acrylic Polymer (N/A); Ethoxydiglyco I (11 1-90-0) ; Tributoxyethyl Phosphate (78-51-3); Dipropylene Glycol Methyl Ether (34590 - 94-8)

#### Storage & Shelf Life:

2 year warranty, Keep from freezing

#### Registrations & Certifications -